



## Optigear BM Range

Gear Oils with MFT

### Description

Castrol Optigear™ BM are solid-free high performance gear oils containing the additive combination Microflux Trans™ (MFT). Designed to reduce wear caused by surface fatigue, pitting, spalling, scuffing, scoring or irregularities during running-in period and during normal operations.

Microflux Trans (TRANS=TRiple Action Non-sacrificial Surface engineering) improves friction surfaces to an extent not possible with normal machining processes and conventional Extreme Pressure (EP) lubricants. In a tribological system, the polarized MFT additives instantaneously create a passive film on friction surfaces before friction occurs. At a given load level, the MFT additives create a resistant protective layer on friction surfaces.

Under severe load, components of the MFT additive combination are activated and diffuse into the surfaces initiating an improvement of their friction characteristics through plastic deformation. The organic reaction products become a component of the tribopolymer system. Unlike the case with conventional lubricants, the tribopolymers formed by MFT are long-chained compounds with excellent lubricity and adhesion. The load carrying area is improved and the hydrodynamic lubrication film is easier to maintain. This unique physical-chemical reaction is Castrol surface engineering and achieves a non-sacrificial micro-smoothing of the friction surfaces.

The MFT additive technology provides optimum wear protection and an extremely low coefficient of friction even under extremes of pressure, vibration, shock loads, at high or low speeds or varying operational conditions.

Optigear BM gear oils are in conformity with and even exceed the requirements of DIN 51517 part 3 CLP and AGMA specifications 9005-D94 for EP Gear Oil.

### Application

In all types of industrial gears, especially operating under extremely heavy loads, where conventional EP oils fail.

- Long term lubrication under the most extreme mechanical conditions, vibrations and elevated temperatures.
- Spur and bevel gears, worm gears up to the medium load range.
- Gears exposed to high sliding friction and high Hertzian surface pressures up to 2000 N/mm<sup>2</sup> (elevators, rolling mills, belt conveyors, extruders, vibrating equipment, crushers, high speed looms and separators).
- Eccentrics, cam shafts and planetary gears.
- Variable speed drives (PIV).
- Sealed gear couplings.
- In all types of bearings, especially for spherical roller bearings, full complement cylindrical roller bearings and thrust bearings.
- Circulation systems.

## Advantages

- Extended life time of machine elements and wear parts, lower maintenance and labour costs by minimised wear and friction.
- Full load operation within shortest time, virtually eliminating the running-in period.
- Lower costs for lubricants and waste oil disposal because of significant extensions of both service life and relubrication intervals.
- Energy savings due to reduced coefficient of friction, lower temperature of lubricant and component and improvement in operating efficiency.
- Product consolidation, i.e. simplification and reduction of lubricants and spare parts.
- Reduction of noise resulting from high frequency stick-slip for "life" lubrication in some applications.
- Smoothing of existing pittings.

## Typical Characteristics

Name	Method	Units	BM150	BM220	BM320	BM460	BM680
Product Code			80012	80013	80014	80015	80016
Colour	Visual	-	Brown	Brown	Brown	Brown	Brown
ISO Viscosity Group	-	-	150	220	320	460	680
AGMA Lubricant No.	-	-	4EP	5EP	6EP	7EP	8EP
Density at 15°C	ISO 12185 / ASTM D4052	g/ml	0.900	0.905	0.910	0.910	0.920
Kin.viscosity at 40°C	ISO 3104 / ASTM D 445	mm <sup>2</sup> /s	150	220	320	460	680
Kin.viscosity at 100°C	ISO 3104 / ASTM D 445	mm <sup>2</sup> /s	15.0	19.4	24.9	31.8	38.3
Viscosity Index	ISO 2909 / ASTM D2270	-	100	100	100	100	93
Flash Point, COC	ISO 2592 / ASTM D92	°C	225 / 437	230 / 446	235 / 455	240 / 464	245 / 473
Pour Point	ISO 3016 / ASTM D97	°C	-18 / 0	-15 / 5	-15 / 5	-12 / -10	-9 / 16
Copper Corrosion (3 hrs at 100°C)	ISO 2160 / ASTM D130	-	1a	1a	1a	1a	1a
Rust Test, Procedure A (24 hrs Distilled Water)	ISO 7210 / ASTM D665	-	Pass	Pass	Pass	Pass	Pass
SRV-Test mode 5 ae: Wear scar diameter	DIN 51834	mm	0.55	0.55	0.55	0.55	0.55
Rust Test, Procedure B (24 hrs Synth Sea Water)	ISO 7210 / ASTM D665	-	Pass	Pass	Pass	Pass	Pass
SRV-Test mode 5 ae: Min. friction coefficient $\mu$	DIN 51834	-	0.06	0.06	0.06	0.06	0.06
SRV-Test mode 5 ae: Max. friction coefficient $\mu$	DIN 51834	-	0.08	0.08	0.08	0.08	0.08
FVA Micro-pitting test, GT-C/ 8.3 at 60 + 90°C	FVA No. 54	-	>10	>10	>10	>10	>10

Subject to usual manufacturing tolerances.

## User Advice

- Miscible and compatible with unleaded gear oils based on mineral oil. However, maximum performance is only guaranteed if not mixed with any other product.
- Compatible with non-ferrous metals.
- Compatible with paints and conventional sealing materials.
- Mechanical cleaning with all known filtering installations and separators possible.

## Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing condition

Optigear BM Range

04 Jun 2012

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

10 Junction Avenue , Parktown , Johannesburg , 2193 , South Africa  
+27 11 488 5111, 0860 222 166 (SA), 0800 111 551 (SA)  
[www.castrol.co.za](http://www.castrol.co.za)