



Hyspin HLP-AF Range

Anti-wear hydraulic oil

Description

The Castrol Hyspin™ HLP-AF range is based upon mineral oil enhanced with an ashless (zinc free) additive system.

Application

Castrol Hyspin HLP-AF is primarily for use in hydraulic equipment, but is suitable for other duties in which lubricants with good oxidation stability and lubrication performance are required. The quality of its base oils and additives permits the application of Hyspin HLP-AF in lightly loaded gears and for use as circulating oil in applications where a rust and oxidation inhibited oil is required.

The range is fully compatible with elastomer materials commonly used for static and dynamic seals, such as nitrile, silicone and fluorinated (e.g. Viton) polymers.

Hyspin HLP-AF is classified as follows:

DIN 51502 classification - HLP ISO 6743/4 - Hydraulic Oils Type HM

Hyspin HLP-AF meets the requirements (for appropriate viscosity grade) of:

DIN 51524 part 2

GB 111118.1 L-HM Hydraulic Oil (Conventional)

Advantages

- Good wear and corrosion protection
- Good thermal and oxidative stability
- High filterability characteristics
- Good water separation

Typical Characteristics

| Name | Method | Units | HLP-AF 32 | HLP-AF 46 | HLP-AF 68 |
|---|--------------------------------------|--------------------|--------------|--------------|--------------|
| Density @ 15°C / 59°F | ISO 12185 / ASTM D4052 / DIN 51757-3 | kg/m ³ | 873 | 881 | 883 |
| Kinematic Viscosity @ 40°C / 104°F | (DIN EN) ISO 3104 / ASTM D445 | mm ² /s | 32 | 46 | 68 |
| Kinematic Viscosity @ 100°C / 212°F | (DIN EN) ISO 3104 / ASTM D445 | mm ² /s | 5.3 | 6.6 | 8.7 |
| Viscosity Index | (DIN) ISO 2909 / ASTM D2270 | - | 94 | 93 | 96 |
| Pour Point | (DIN) ISO 3016 / ASTM D97 | °C/°F | -27/-17 | -24/-11 | -24/-11 |
| Foam Sequence I - tendency / stability | ISO 6247 / ASTM D882 | ml/ml | 30/0 | 30/0 | 30/0 |
| Flash Point - open cup method | ISO 2592 / ASTM D92 | °C/°F | 210/410 | 225/437 | 230/446 |
| Water Separation @ 54°C / 129°F (40/37/3) | (DIN) ISO 6614 / ASTM D1401 | mins | 10 | 15 | 10 |
| Air Release @ 50°C / 122°F | (DIN) ISO 9120 / ASTM D342 | mins | 4 | 6 | 8 |
| Copper corrosion 3h @ 100°C / 212°F | (DIN EN) ISO 2160 / ASTM D 130 | Class | 1 | 1 | 1 |
| Rust test - distilled water (24 hrs) | (DIN) ISO 7120 / ASTM D665A | Rating | Pass | Pass | Pass |
| Water content (%) | (DIN EN) ISO 12937 / ASTM D95 | %wt | Trace, max | | |
| FZG Gear Scuffing test - A/8.3/90 | (DIN) ISO 14635-1 | Failure Load Stage | >11 | | |

Subject to usual manufacturing tolerances.

Hyspin HLP-AF Range

09 Mar 2020

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

199 Oxford Road, Dunkeld, Johannesburg, 2196, South Africa
 +27 11 488 5111, 0860 222 166 (SA), 0800 111 551 (SA)
www.castrol.co.za